

corr. US 5,985,973

## EUROPEAN PATENT OFFICE

### Patent Abstracts of Japan

PUBLICATION NUMBER : 11071431  
PUBLICATION DATE : 16-03-99

APPLICATION DATE : 01-08-97  
APPLICATION NUMBER : 09208120

APPLICANT : IDEMITSU PETROCHEM CO LTD;

INVENTOR : YAMADA MOTOKI;

$$100y / [y \times (1 - x / 100) + x] \leq 1.13z - 16.6$$

INT.CL. : C08F210/06 C08K 3/34 C08L 23/10  
//(C08L 23/10 , C08L 23:16 )

TITLE : POLYPROPYLENE-BASED RESIN AND  
POLYPROPYLENE-BASED RESIN  
COMPOSITION

ABSTRACT : PROBLEM TO BE SOLVED: To obtain a polypropylene-based resin composition improved in flowability, rigidity, tensile elongation at break and impact resistance by mixing a polypropylene-based resin specified in melt index, xylene-solubles content, etc., with an ethylene and/or  $\alpha$ -olefin copolymer and talc.

SOLUTION: This composition comprises 45-90 wt.% polypropylene resin characterized in that the MI is 30-70 g/10 min, the content (x) of xylene solubles at 25°C is 5-15 wt.%, the ethylene unit content (z) as determined by the isotope carbon nuclear magnetic resonance spectroscopy ( $^{13}\text{C}$ -NMR) is 2.00 dl/g or above, the content of viscosity (at 135°C in decalin) is 2.00 dl/g or above, the content of xylene insolubles at 25°C and the ethylene unit content (y wt.%) as determined by the  $^{13}\text{C}$ -NMR satisfy the relationship, the content of components having molecular weights of  $10^6$  or above in a molecular weight distribution curve in terms of the polystyrene as determined by gel permeation chromatography is 2 wt.% or above, the MI is 40-130 g/10 min or above, etc., 5-50 wt.% copolymer based on ethylene and/or an  $\alpha$ -olefin and 0-25 wt.% talc.

COPYRIGHT: (C)1999,JPO

## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **11071431 A**(43) Date of publication of application: **16.03.99**

(51) Int. Cl.

**C08F210/06**  
**C08K 3/34**  
**C08L 23/10**  
**/(C08L 23/10 , C08L 23:16 )**

(21) Application number: **09208120**(22) Date of filing: **01.08.97**

(30) Priority: **16.08.96 JP 08216201**  
**18.06.97 JP 09161525**

(71) Applicant: **IDEMITSU PETROCHEM CO LTD**

(72) Inventor: **SUMITOMO KOJI**  
**NAKAGAWA SUSUMU**  
**TODA MASATOSHI**  
**KOBAYASHI YUTAKA**  
**YAMADA MOTOKI**

(54) **POLYPROPYLENE-BASED RESIN AND**  
**POLYPROPYLENE-BASED RESIN COMPOSITION**

(57) Abstract:

**PROBLEM TO BE SOLVED:** To obtain a polypropylene-based resin composition improved in flowability, rigidity, tensile elongation at break and impact resistance by mixing a polypropylene-based resin specified in melt index, xylene-solubles content, etc., with an ethylene and/or  $\alpha$ -olefin copolymer and talc.

**SOLUTION:** This composition comprises 45-90 wt.% polypropylene resin characterized in that the MI is 30-70 g/10 min, the content (x) of xylene solubles at 25°C is 5-15 wt.%, the ethylene unit content (z) as determined by the isotope carbon nuclear magnetic resonance spectroscopy ( $^{13}\text{C}$ -NMR) is 2.00 dl/g or above, the content of viscosity (at 135°C in decalin) is 2.00 dl/g or above, the content of xylene insolubles at 25°C and the ethylene unit content (y wt.%) as determined by the  $^{13}\text{C}$ -NMR satisfy the relationship, the content of components having molecular weights of  $10^6$  or above in a molecular weight distribution curve in terms of the polystyrene as determined by gel permeation chromatography is 2 wt.% or above, the MI is 40-130 g/10 min or above, etc., 5-50 wt.% copolymer based on ethylene and/or an  $\alpha$ -olefin and 0-25 wt.% talc.

$$100y / [y \times (1 - x/100) + x] \leq 1.13z - 16.6$$